

3M™ Heat Shrinkable Marker Sleeve FP-303MS

Flexible Polyolefin Heat Shrinkable Tubing

Data Sheet

January 2010

Description 3M™ Heat Shrinkable Marker Sleeve FP-303MS offers an outstanding balance of electrical, physical and chemical properties for a wide variety of industrial applications. Available in continuous spools, the Heat Shrinkable Marker Sleeve FP-303MS tubing is designed for computer-based printing using the 3M Thermal Roll Printer TRP-303.

3M™ Heat Shrinkable Marker Sleeve FP-303MS has a 3:1 shrink ratio. When freely recovered, the tubing will shrink to 33% of its as-supplied internal diameter. The recovered wall thickness is proportional to the degree of recovery. Minimum shrink temperature is 212°F (100°C). The operating is -67° to 275°F (-55° to +135°C)

Agency Approvals & Self Certifications


Meets the material requirements of SAE-AMS-DTL-23053/5*

- Meets the Marker Permanence requirements of:
 - SAE-AS81531 (20 rubs) and
 - MIL-STD-202 Method 215K - (10 rubs x 3 cycles each fluid)
- Isopropyl Alcohol / Mineral Spirits
- Terpene Defluxer
- H2O / PGME / Monoethanolamine

When used with 3M Thermal Roll Printer Black Ribbon RBN-BLK series

- UL Recognized, File E-39100, at 600 volts maximum @ 125°C
- CSA Certified, CSA LR38227, at 600 volts maximum @ 125°C

*Formerly MIL-I-23053/5 and MIL-DTL-23053/5

RoHS 2002/95/EC 

RoHS Compliant 2002/95/EC" means that the product or part ("Product") does not contain any of the substances in excess of the maximum concentration values in EU Directive 2002/95/EC, as amended by Commission Decision 2002/618/EC, unless the substance is in an application that is exempt under RoHS. This information represents 3M's knowledge and belief, which may be based in whole or in part on information provided by third party suppliers to 3M.

3M™ Heat Shrinkable Marker Sleeve

Typical Properties

Not for specifications. Values are typical, not to be considered minimum or maximum.
Properties measured at room temperature 73°F (~23°C) unless otherwise stated.

Physical

Property	Typical Value US units (metric)
Tensile Strength	2400 psi
Elongation (% at break)	400%
Longitudinal change	+5% -15%
Specific Gravity	1.3 (Opaque) .93 (Clear)
Operating Temperature	-67°to 275°F (-55°to +135°C)
Shrink Temperature (minimum)	212°F (100°C)
Heat Aging (336 hrs. @ 175°C)	Elongation 175%
Heat shock (4 hrs. @ 250°C)	No dripping, flowing, cracking, passes mandrel wrap test
Low Temperature Flexibility (4 hrs @ -55°C)	No cracking
Secant Modulus (2%)	13,000 psi
Flammability Self-extinguish, Meets UL 224 All-Tubing Flame Test (Except Clear)	Pass

Electrical

Property	Typical Value
Dielectric Strength	900 V/mil
Volume Resistivity	10 ¹⁵ ohm-cm

Chemical

Property	Typical Value
Corrosive Resistance	Non-corrosive
Solvent Resistance	Excellent
Water Absorption	0.2%
Fungus Resistance	Non-nutrient

3M™ Heat Shrinkable Marker Sleeve

Standard Sizes and Dimensions	Ordering Size	Expanded I.D. (Minimum) in. (mm)	Recovered I.D. (Maximum) in. (mm)	Recovered Wall Thickness (Nominal) in. (mm)
	1/8	.125 (3,2)	.043 (1,1)	.024 (0,6)
3/16	.188 (4,8)	.063 (1,6)	.026 (0,65)	
1/4	.250 (6,4)	.083 (2,1)	.028 (0,7)	
3/8	.375 (9,5)	.122 (3,1)	.031 (0,8)	
1/2	.500 (12,7)	.165 (4,2)	.033 (0,85)	
3/4	.750 (19,1)	.248 (6,3)	.039 (1,0)	
1	1.000 (25,4)	.327 (8,3)	.048 (1,2)	

Recommended Sizing Application Range

Ordering Size	Wire Diameter Range	Nominal THHN Wire Size
1/8	0.046" – 0.106" (1.16mm – 2.70mm)	22 – 16 AWG
3/16	0.069" – 0.159" (1.74mm – 4.04mm)	18 – 12 AWG
1/4	0.092" – 0.213" (2.33mm – 5.40mm)	16 – 10 AWG
3/8	0.138" – 0.319" (3.49mm – 8.10mm)	10 – 6 AWG
1/2	0.183" – 0.425" (4.66mm – 10.80mm)	8 – 2 AWG
3/4	0.275" – 0.638" (6.99mm – 16.19mm)	6 – 3/0 AWG
1	0.367" – 0.850" (9.31mm – 21.59mm)	2 AWG – 350 MCM

Shelf Life & Storage This product has a 10-year shelf life from date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity).

Availability Please contact your local distributor; available from 3M.com/electrical [Where to Buy] or call 1-800-676-8381.

Important Notice All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.

3M is a trademarks of 3M Company.



Electrical Markets Division

6801 River Place Blvd.
Austin, TX 78726-9000
800 676 8381
FAX: 800 828 9329
www.3M.com/electrical

Please recycle
© 3M 2010 All rights reserved
78-8127-9808-6 A